



CP06-N0009

Polyamide 6

30% Glass Bead Reinforcement, Heat Stabilized

5401 N Hwy 41 / Suite 1000 Evansville, IN 47711 • Phone: 812.426.1350 • FAX: 888.855.3671 • www.cpptech.com

Physical	Method	Typical Value	Units
Specific Gravity	ASTM D792	1.35	
Mold Shrink, Flow: 0.125 in	ASTM D955	0.003	in/in
Impact			
Notched Izod Impact (.125 in) 73°F	ASTM D256	0.8	ft-lbs/in
Mechanical			
Tensile Modulus	ASTM D638	655,000	psi
Tensile Strength @ Break	ASTM D638	10,500	psi
Tensile Elongation @ Break	ASTM D638	8.0	%
Thermal			
Deflection Temperature Under Load 66 psi	ASTM D648	360	°F

Information provided is based on typical values from reliable procedures. Values are based on natural or black materials unless otherwise noted. No guarantees or warranties of any kind are expressed or implied. Users are responsible for determining the suitability of the product for their intended application.

Recommended Processing Parameters

Drying Temperature	180°F
Drying Time	2.0 - 4.0 Hours
Suggested Max Moisture	.10%
Processing (Melt) Temperature	480 - 550 °F
Mold Temperature	150 - 200 °F

CPPT recommended processing parameters are meant to serve as guidelines only and are not intended to be used for specification purposes. Conditions should be adjusted to optimize material performance with the equipment part design and tooling.