



CP06-N0020

Polyamide 6

33% Hydrolysis Resistant Glass Fiber Reinforcement

Heat Stabilized, w/ Lube

5401 N Hwy 41 / Suite 1000 Evansville, IN 47711 • Phone: 812.426.1350 • FAX: 888.855.3671 • www.cpptech.com

Physical	Method	Typical Value	Units
Specific Gravity	ASTM D792	1.39	
Mold Shrink, Flow: 0.125 in	ASTM D955	0.004	in/in
Impact			
Notched Izod Impact (.125 in) 73°F	ASTM D256	1.7	ft-lbs/in
Mechanical			
Tensile Strength @ Yield	ASTM D638	22,000	psi
Tensile Elongation @ Break	ASTM D638	3.0	%
Flexural Strength	ASTM D790	35,000	psi
Flexural Modulus	ASTM D790	1,200,000	psi
Thermal			
Deflection Temperature Under Load			
66 psi	ASTM D648	420	°F
264 psi	ASTM D648	401	°F

Information provided is based on typical values from reliable procedures. Values are based on natural or black materials unless otherwise noted. No guarantees or warranties of any kind are expressed or implied. Users are responsible for determining the suitability of the product for their intended application.

Recommended Processing Parameters

Drying Temperature	180°F
Suggested Maximum Moisture Content	0.15%
Drying Time	2.0 - 4.0 Hours
Processing (Melt) Temperature	510 - 560 °F
Mold Temperature	170 - 210 °F

CPPT recommended processing parameters are meant to serve as guidelines only and are not intended to be used for specification purposes. Conditions should be adjusted to optimize material performance with the equipment part design and tooling.