



**CP07-N0014**

**Polyamide 66**

15% Glass Fiber Reinforcement, Heat Stabilized, w/ Lube

5401 N Hwy 41 / Suite 1000 Evansville, IN 47711 • Phone: 812.426.1350 • FAX: 888.855.3671 • www.cpptech.com

Physical	Method	Typical Value	Units
Specific Gravity	ASTM D792	1.23	
Mold Shrink, Flow: 0.125 in	ASTM D955	0.008	in/in

**Impact**

Notched Izod Impact (.125 in) 73°F	ASTM D256	1.2	ft-lbs/in
---------------------------------------	-----------	-----	-----------

**Mechanical**

Tensile Strength @ Yield	ASTM D638	15,000	psi
Tensile Elongation @ Break	ASTM D638	4.0	%
Flexural Modulus	ASTM D790	775,000	psi

**Thermal**

Deflection Temperature Under Load 264 psi	ASTM D648	460	°F
--	-----------	-----	----

Information provided is based on typical values from reliable procedures. Values are based on natural or black materials unless otherwise noted. No guarantees or warranties of any kind are expressed or implied. Users are responsible for determining the suitability of the product for their intended application.

**Recommended Processing Parameters**

Drying Temperature	180°F
Drying Time	3.0 - 4.0 Hours
Suggested Maximum Moisture Content	0.15%
Rear Temperature	480 - 550 °F
Middle Temperature	480 - 550 °F
Front Temperature	480 - 550 °F
Nozzle Temperature	480 - 550 °F
Processing (Melt) Temperature	480 - 550 °F
Mold Temperature	160 - 220 °F

CPPT recommended processing parameters are meant to serve as guidelines only and are not intended to be used for specification purposes. Conditions should be adjusted to optimize material performance with the equipment part design and tooling.