



**CP09-N0115**

**Polycarbonate**

10% Glass Fiber Reinforcement

Good Impact Strength, Flame Retardant, w/ Release

5401 N Hwy 41 / Suite 1000 Evansville, IN 47711 • Phone: 812.426.1350 • FAX: 888.855.3671 • www.cpptech.com

Physical	Method	Typical Value	Units
Melt Flow	ASTM D1238	12	g/10 min
Specific Gravity	ASTM D792	1.25	
Mold Shrink, Linear Flow (.125 in)	ASTM D955	0.004	in/in

**Impact**

Notched Izod Impact (.125 in) 73°F	ASTM D256	2.2	ft-lbs/in
---------------------------------------	-----------	-----	-----------

**Mechanical**

Tensile Strength @ Yield	ASTM D638	9,200	psi
Tensile Elongation @ Break	ASTM D638	14	%
Flexural Strength	ASTM D790	14,500	psi
Flexural Modulus	ASTM D790	500,000	psi

**Thermal**

Deflection Temperature Under Load .250 in, 66 psi	ASTM D648	293	°F
.250 in, 264 psi	ASTM D648	286	°F

**Flammability**

Flame Rating @ .0625 in	UL 94	V-0	-
Flame Rating @ .125 in	UL 94	5VA	-

Information provided is based on typical values from reliable procedures. Values are based on natural or black materials unless otherwise noted. No guarantees or warranties of any kind are expressed or implied. Users are responsible for determining the suitability of the product for their intended application.

**Recommended Processing Parameters**

Drying Temperature	250°F
Drying Time	2.0 - 4.0 Hours
Suggested Maximum Moisture Content	0.02%
Rear Temperature	530 - 580 °F
Middle Temperature	550 - 590 °F
Front Temperature	570 - 610 °F
Nozzle Temperature	570 - 610°F
Processing (Melt) Temperature	570 - 610°F
Mold Temperature	180 - 240°F

CPPT recommended processing parameters are meant to serve as guidelines only and are not intended to be used for specification purposes. Conditions should be adjusted to optimize material performance with the equipment part design and tooling.