



CP55-N0018

PPE+PS+PA

Increased Heat Stability, Paintable, Medium Flow

5401 N Hwy 41 / Suite 1000 Evansville, IN 47711 • Phone: 812.426.1350 • FAX: 888.855.3671 • www.cpptech.com

Physical	Method	Typical Value	Units
Melt Flow (280°C / 2.16kg)	ASTM D1238	2.0	g/10 min
Melt Flow (280°C / 5.0kg)	ASTM D1238	5.5	g/10 min
Specific Gravity	ASTM D792	1.08	
Mold Shrink, Flow: 0.125 in	ASTM D955	0.012	in/in
Rockwell Hardness (R-scale)	ASTM D785	115	R

Impact

Notched Izod Impact (.125 in) 73°F (23°C)	ASTM D256	4.5	ft-lbf/in
Notched Izod Impact (.125 in) -22°F (-30°C)	ASTM D256	2.0	ft-lbf/in
Notched Izod Impact (.125 in) -40°F (-40°C)	ASTM D256	1.0	ft-lbf/in
Gardner Impact (.125 in) 73°F (23°C)	ASTM D5420	240	in-lbs

Mechanical

Tensile Strength @ Yield	ASTM D638	7,900	psi
Tensile Elongation @ Break	ASTM D638	40.0	%
Flexural Strength	ASTM D790	12,500	psi
Flexural Modulus	ASTM D790	330,000	psi

Thermal

Deflection Temperature Under Load			
.250 in, 66 psi	ASTM D648	329	°F
.250 in, 264 psi	ASTM D648	255	°F

Information provided is based on typical values from reliable procedures. Values are based on natural or black materials unless otherwise noted. No guarantees or warranties of any kind are expressed or implied. Users are responsible for determining the suitability of the product for their intended application.

Recommended Processing Parameters

Drying Temperature	225°F
Drying Time	3.0 - 5.0 Hours
Suggested Maximum Moisture Content	0.07%
Rear Temperature	480 - 560 °F
Middle Temperature	500 - 560 °F
Front Temperature	510 - 560 °F
Nozzle Temperature	520 - 560 °F
Processing (Melt) Temperature	520 - 560 °F
Mold Temperature	150 - 200 °F
Mold Temperature	140 - 200 °F

CPPT recommended processing parameters are meant to serve as guidelines only and are not intended to be used for specification purposes. Conditions should be adjusted to optimize material performance with the equipment part design and tooling.